

GGS 270HP Woven

GGS 270HP is a woven geotextile made of 100% high tenacity polypropylene yarns which are woven into a stable network such that the yarns retain their relative position. GGS 270HP resists ultraviolet deterioration, rotting, biological degradation, naturally encountered basics and acids. Polypropylene is stable within a pH range of 2 to 13. GGS 270HP meets or exceeds the physical property values listed below:

Property	Test Method	Unit	M.A.R.V
Wide Width Tensile	ASTM D 4595	lbs/ft	2640 x2460
Wide Width Tensile			
(2% Strain)	ASTM D 4595 •	lbs/ft •	480 x588
Wide Width Tensile			
(5% Strain)	ASTM D 4595	lbs/ft	1212 x1356
Wide Width Tensile	107115 1707	п и	2012 2112
(10% Strain)	ASTM D 4595	lbs/ft	2340 x2412
Permeability	ASTM D 4491	cm/sec	.04
Permittivity	ASTM D 4491	sec -1	0.70
Water Flow	ASTM D 4491	gpm/sf	50
AOS	ASTM D 4751	US Std Sieve	30
UV Resistance	ASTM D 4355	%/hours	80/500hrs